

Amendments to the Claims:

This listing of claims will replace all prior versions, and listings, of claims in the application:

Listing of Claims:

Claims 1-19 (canceled).

20. (previously presented) Aluminium alloy exhibiting high strength and low quench sensitivity comprising

4.6	to	5.2	wt. % Zn
2.6	to	3.0	wt. % Mg
0.1	to	0.2	wt. % Cu
0.05	to	0.2	wt. % Zr
max.		0.05	wt. % Mn
max.		0.05	wt. % Cr
max.		0.15	wt. % Fe
max.		0.15	wt. % Si
max.		0.10	wt. % Ti

the remainder being impurities due to the manufacturing process, individually at maximum 0.05 wt.%, in total at maximum 0.15 wt.%.

21. (previously presented) Aluminium alloy according to claim 20, comprising 4.6 to 4.8 wt. % Zn.

22. (previously presented) Aluminium alloy according to claim 21, comprising 2.6 to 2.8 wt.% Mg.

23. (previously presented) Aluminium alloy according to claim 22, comprising 0.10 to 0.15 wt.% Cu.

24. (previously presented) Aluminium alloy according to claim 23, comprising 0.08 to 0.18 wt.% Zr.

25. (previously presented) Aluminium alloy according to claim 24, including a maximum concentration of 0.03 wt.% Mn.

26. (previously presented) Aluminium alloy according to claim 24, including a maximum concentration of 0.02 wt.% Cr.

27. (previously presented) Aluminium alloy according to claim 24, including a maximum concentration of 0.12 wt.% Fe.

28. (previously presented) Aluminium alloy according to claim 24, including a maximum concentration of 0.12 wt.% Si.

29. (previously presented) Aluminium alloy according to claim 24, including a maximum concentration of 0.05 wt.% Ti.

Appln. SN 10/541,788
Amdt. Dated December 27, 2007
Reply to Office Action of December 4, 2007

30-37. (canceled).